

NEW METHOD FOR CONTROLLABLE ACCELERATED AGING OF MARBLE: USE FOR TESTING OF CONSOLIDANTS

Enrico Sassoni¹, Gabriela Graziani¹, Elisa Franzoni¹, George W. Scherer²

¹ Dept. Civil, Chemical, Environmental and Materials Engineering (DICAM), University of Bologna, Italy

² Dept. Civil and Environmental Engineering (CEE), Princeton University, USA

ABSTRACT

Research is needed on novel consolidants to restore weathered marble, because the available products exhibit limitations. To test new consolidants, samples with features similar to naturally weathered marble (i.e. near-surface damage) are recommended. We developed a novel method that produces decayed samples with a gradient in properties that can be tuned to any desired level, in terms of depth from the surface and decrease of dynamic elastic modulus. The idea is to produce near-surface damage by putting a marble sample in contact with a plate at a certain temperature for a certain time, calculated by a mathematical model. The model was used to predict the heating conditions to produce a certain decrease in dynamic elastic modulus in the first 1 cm from the surface, comparable to naturally weathered marble. Good confirmation of the model predictions was found experimentally. The suitability of using thermally “weathered” samples for testing consolidants was demonstrated in the case of a hydroxyapatite-based treatment. The mathematical model can be tailored to other lithotypes or ceramics, using the relevant property data.

KEYWORDS

Aging; Calcium phosphate; Consolidation; Cracks/cracking; Hydroxyapatite

1. INTRODUCTION

Marble is one of the most used materials in historic architecture and is still widely used to clad building façades. Unfortunately, marble is highly sensitive to thermal weathering, because it consists of calcite crystals that exhibit highly anisotropic thermal expansion¹. Repeated heating-cooling cycles (such as day/night temperature variations) induce stress at grain boundaries and open new micro-cracks when the cohesion among grains is exceeded. This leads to the detachment of grains (the so-called "sugaring" phenomenon²), that may lead to the loss of several mm of material from the surface³⁻⁵, and to bowing of cladding slabs that may eventually fracture and fall down⁶⁻⁹. As a consequence of micro-crack formation, water can penetrate into marble and trigger additional weathering phenomena, such as dissolution at grain boundaries, freeze-thaw cycles, and salt crystallization cycles.

Several types of consolidants have been tested through the years, with the aim of bonding loose calcite grains and restoring mechanical properties¹⁰⁻¹². However, research on consolidants is still in progress, because the products currently available in the market are not fully satisfactory, owing to problems such as inadequate penetration, coloration, and insufficient adhesion¹³. The development of new consolidants requires the use of suitable samples for testing the new materials. Naturally weathered samples are usually not available in sufficient quantity and with sufficiently uniform characteristics. Unweathered samples lack micro-cracks at grain boundaries, so that the ability of a consolidant to penetrate deeply into cracks and bond the crack surfaces cannot be assessed reliably¹⁴. Consequently, the use of artificially weathered samples is preferable. Several methods for artificial weathering of stone have been developed, including freeze-thaw cycles, salt crystallization cycles, acid attack, and mechanical pre-stress¹⁵⁻¹⁸. However, the suitability of these methods depends on the type of stone, its microstructure, and the type of weathering that one

intends to reproduce. In the case of carbonate stones, such as marble and limestone, in previous studies we showed that an effective way to induce new micro-cracks at grain boundaries, without causing contamination of the samples by salts or other residues, is to heat the stone to high temperature (300-400 °C) in an oven, to exploit the anisotropic thermal behavior of calcite crystals^{13,15,19}. The newly formed micro-cracks lead to an increase in open porosity and water absorption and a decrease in cohesion resulting in a loss of stiffness and strength^{15,19}. Notably, the damaging effect obtained by heating is sensibly greater for stones with low initial porosity, such as marble, because in porous stones the existing voids allow some deformation of calcite crystals without causing as much stress at the grain boundaries and consequently reduce formation of new micro-cracks¹⁹. However, this procedure has the limitation that so-obtained samples are uniformly weathered, i.e. they do not exhibit the gradient in properties that characterizes naturally weathered marble. For instance, the analysis of a marble element, which had been exposed outdoors for some 150 years, revealed strong decohesion of grains (measured by ultrasound) in the first 1 cm from the surface, with only a modest decay between 1 and 2 cm and no damage at greater depth²⁰.

In this paper, we propose a novel method that provides decayed samples with a gradient in properties that can be tuned to any desired level, in terms of depth from the surface and magnitude of decrease in dynamic elastic modulus (which can be taken as indicative of mechanical damage, as detailed in the following). The method is based on the idea of producing near-surface damage by putting a marble sample in contact with a hot plate for a certain time. In this way, the damage is not uniform (unlike the case of samples heated in an oven), but the part closest to the plate experiences the greatest damage. It is true that such samples lack some of the features exhibited by naturally weathered marble, often also affected by additional weathering phenomena (such as dissolution at grain boundaries); however, inducing realistic micro-crack formation is regarded as the most important aspect, because thermal damage represents the first and often the most

important stage of marble deterioration in the field. The heating temperature and time necessary to reach a certain level of decay can be calculated by a mathematical model that takes into account how the thermal diffusivity (k) and the dynamic elastic modulus (E_d) of the lithotype change with temperature. The mathematical model is first presented and the experimental tests used to evaluate the temperature dependence of k and E_d are described. The model is then validated through an example of its application to produce damage to two different levels and the suitability of using so-obtained samples for testing an innovative consolidant is finally illustrated.

2. THEORETICAL MODELING

For a marble sample put onto a hotplate at a certain initial temperature, the heat flow is governed by:

$$\frac{\partial T}{\partial t} = \frac{\partial}{\partial x} \left(k[x, t] \frac{\partial T}{\partial x} \right) \quad (1)$$

where T is the temperature, t is the time, x is the distance from the heating plate and k is the thermal diffusivity. If heat losses are prevented by insulating the top and the sides of the sample, the boundary conditions are zero flux at the top (insulated) surface and $T[0, t]$ measured at the surface in contact with the hotplate. In the present case, k decreases as temperature increases, because micro-cracks that are formed at grain boundaries impede heat flow²¹. As a first approximation, the temperature dependence of k was assumed to be exponential, based on the data reported in the literature for a different type of marble²¹:

$$k[x, t] = k_1 + k_2 \exp \left[- \lambda_k T[x, t] \right] \quad (2)$$

where k_1 , k_2 and λ_k are constants. An analogous equation,

$$E_d = E_0 \exp\left[-\frac{1}{E} T\right] \quad (3)$$

describes the temperature dependence of the dynamic elastic modulus, as shown in § 4.2. However, it has been demonstrated experimentally that cooling does at least as much damage as heating²², so the simple dependence on T in Eq. (2) is only a convenient approximation to describe heating cycles. Better results are obtained by relating k to the strain energy in the body, as shown in § 4.3, but a small improvement comes at the cost of considerable complexity.

Fitting $T[x,t]$ for all of the runs simultaneously with a single set of parameters resulted in much poorer fits than when fitting each run individually. This was ascribed to the fact that fast heating creates macroscopic thermal stress, because hotter regions are under compressive stress in the plane of the hot plate (owing to constraint by the cooler inner regions). Therefore, the fit was repeated by performing simultaneous fits to experiments of both slow and fast heating, allowing the thermal diffusivity to depend on strain energy density, Φ , according to the equation:

$$k = k_1 + k_2 \mathcal{Y}[F] \quad (4)$$

where the function ψ is shown in § 4.1. Based on our experimental observation that E_d and the thermal expansion coefficient, α , of marble show the same temperature dependence, and lacking any theoretical justification for a different choice, we assume that the same function governs all three properties:

$$\mathcal{Y}[F] = \frac{k[F] - k_1}{k_2} = \frac{E_d[F] - E_0}{E_0} = \frac{\alpha_1 - \alpha[F]}{\alpha_2} \quad (5)$$

where the subscripted parameters are constants.

The procedure for finding $\psi[\Phi]$ is explained in detail in the Supplementary Material.

Briefly, we begin by recognizing that each grain of calcite undergoes highly anisotropic dimensional change as the temperature rises or falls, but the grain is constrained within a polycrystalline matrix with a more or less isotropic expansion coefficient. (The linear thermal expansion coefficient of calcite, in units of $10^{-6}/^{\circ}\text{C}$, is about +25 along the c-axis and -5.6 normal to the c-axis, for a volumetric average of +4.6, while the value for polycrystalline rocks is in the range of 8 ± 4 ²³.) Walsh has analyzed the effect of strain energy on expansion of marble, but his equations apply to small temperature intervals, where the opening of grain boundaries does not influence the thermal or elastic properties²³. We regard the latter properties as highly important, so we employ a simplified geometric model to take them into account: we treat an individual grain of calcite as a sphere with a linear expansion of $4.6 \times 10^{-6}/^{\circ}\text{C}$ surrounded by an isotropic matrix whose properties vary with temperature; the latter are taken from our direct measurements on Carrara marble. If the sample is heated rapidly, there are additional stresses from the macroscopic temperature gradient that are easily calculated. Their effect can be included by imposing the hydrostatic component of those stresses on the outer surface of the composite sphere model, as explained in the Supplementary Material. Obviously, this is a highly approximate model, because the calcite grain is not a sphere, and it has highly anisotropic thermal and elastic properties, so that expansion results in local shear stresses that are neglected; moreover, the anisotropy of the polycrystalline matrix is ignored. Nevertheless, the fact that the model adequately reproduces the temperature distribution inside the sample, which depends on the evolving $k[x,t]$, indicates that the model roughly captures the influence of stress on heat transfer and consequent damage.

To relate the strain energy to the changes in physical properties, we make use of the theory of Budiansky and O'Connell²⁴, which predicts the influence of cracks at grain boundaries on the

elastic properties of a body. The analysis proceeds as follows (the details are explained in the Supplementary Material):

- (i) From the change in E_d with temperature following isothermal treatments, we can use the theory²⁴ to infer the crack density, $\rho[T]$.
- (ii) The theory²⁴ predicts the bulk and shear moduli and Poisson's ratio in the damaged material as functions of ρ .
- (iii) Using those properties, together with the measured thermal expansion coefficient, in the composite sphere model, we find Φ as a function of T (in the absence of a temperature gradient); then we can establish the functional dependence of ρ on Φ .
- (iv) Given $E_d[T]$ from experiment, $\rho[T]$ from (i), and $\rho[\Phi]$ from (iii), we can find $\psi[\Phi]$ from Eq. (5)

Calculation of stresses created by rapid heating requires iteration, because the strain energy depends on the moduli, and the moduli depend on the strain energy. In the first iteration, we use Eqs. (2) and (3); subsequent iterations use properties from Eq. (5) with Φ from the preceding iteration. A satisfactory result for $\psi[\Phi]$ is obtained after 4 iterations. A joint fit to all of the data sets using Eq. (5) results in fits to the temperature that are similar to those obtained from individual fits to each set using Eq. (2). The results are summarized in § 4.3.

The dynamic elastic modulus E_d was adopted as a reliable parameter to describe the damage caused by heating, because in marbles E_d has been demonstrated to be highly sensitive to formation of micro-cracks^{25,26} and quantitative correlations have been established between E_d and strength (although the scatter is significant)^{27,28}.

Once the temperature change with time and distance from the plate can be predicted from the model, and the decrease in E_d can be related to that temperature change, it is possible to

calculate what heating temperature and time will lead to a certain profile in E_d . An example of the model application is presented in § 4.3.

3. EXPERIMENTAL PROCEDURE

3.1. Marble

Experimental tests were carried out on $5 \times 5 \times 1$ cm³ prismatic samples of Carrara marble, sawn from a slab provided by BasketweaveMosaics.com (USA). This lithotype is a white variety of marble quarried in Carrara (Italy), which has been widely used in historic architecture and sculpture, so that it is likely the most widely studied type of marble in the literature^{1,5,7,8,14,19,20}. It is composed of calcite grains, with only ppm impurities (mainly dolomite), and it has very low open porosity (<0.2%)²⁹. An SEM image illustrating marble microstructure and grain size (obtained by acid etching of a polished surface to expose the grain boundaries) is reported in Figure 1.

3.2. Temperature dependence of the thermal diffusivity

The thermal diffusivity was determined by putting marble samples onto a hotplate at a certain initial temperature and measuring the variation in temperature inside the sample as a function of time and distance from the plate. To measure the temperature inside the sample, grooves were cut in a $5 \times 5 \times 1$ cm³ marble sample to allow the insertion of thermocouples to measure the marble temperature at increasing distance from the heating plate. First, the grooves (1 mm thickness) were cut in 4 different samples (Figure 2a), then the samples with the grooves were coupled with 4 other samples without grooves, so as to obtain 4 “sandwich samples” (Figure 2b). The sandwiches were held together by a layer of insulating materials (described below) and an external band of tape. Finally, a thermocouple was inserted into each groove (so as to reach a

distance of 1, 2, 3 and 4 cm from the hotplate), while 2 additional thermocouples were used to measure the temperature at the contact point of the sample with the hotplate (distance = 0 cm) and on top of the sample (distance = 5 cm), as illustrated in Figure 2c. The 6 thermocouples were then connected to an acquisition system (IOtech Personal Daq/56 and DASyLab V 7.00.05 software).

To prevent heat losses, the sides and the top of the “sandwich samples” were wrapped with a high-temperature-resistant insulator (Insulfrax S Blanket, kindly supplied by McNeil Inc.), not illustrated in Figure 2c for readability’s sake. Four different experiments were run: three of “slow heating” from room temperature to 400 °C (2 samples) or 200 °C (1 sample) and one of “fast heating” from 200 °C to 400 °C (400 °C being the maximum temperature that the thermocouples could read). In all experiments, the temperature increase as a function of time and distance from the plate was measured. Then, by solving Eq. (1) numerically and fitting to the experimental data, the parameters k_1 , k_2 and λ_k were obtained.

The analysis was performed by solving Eq. (1) with the NDSolve routine in Mathematica[®] (Mathematica v. 11.0, Wolfram Research, Inc., Champaign, Illinois, 2016) with properties given by Eq. (5). The parameters were adjusted using a simplex scheme³⁰ to obtain the best fit to the measured temperature and time data.

3.3. Temperature dependence of dynamic elastic modulus

The correlation between T and E_d was determined by heating $5 \times 5 \times 1$ cm³ marble samples at 100, 200, 300 and 400 °C for 1 hour in an oven and then measuring the resulting decrease in ultrasonic pulse velocity, v . E_d was calculated according to the formula $E_d = d v^2$, where d is the density of the marble (2670 kg/m³). The velocity was measured across the 5 cm sides of the samples using a PUNDIT instrument with 54 kHz transducers and a rubber couplant between the sample and the transducers.

3.4. Consolidation

The suitability of the artificially weathered samples, obtained as described above, to test new consolidants for marble was evaluated as follows. Two samples heated at 200 °C for 20 sec and two samples heated at 300 °C for 20 sec were treated using a phosphate consolidant. This treatment is based on the idea of bonding the surfaces of cracks between calcite grains by forming hydroxyapatite (HAP, $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$) inside the cracks¹³. HAP is formed by impregnating marble with an aqueous solution of diammonium hydrogen phosphate (DAP, $(\text{NH}_4)_2\text{HPO}_4$)¹³. Samples were treated with the most recent formulation of the HAP-treatment³¹, consisting in a 0.1 M DAP solution also containing 0.1 mM CaCl_2 (added to increase marble coverage by HAP^{32,33}) and 10 vol% ethanol (added to favor HAP formation even at low DAP concentrations^{34,35}). Samples were treated by vacuum impregnation, to ensure penetration of the DAP solution into the micro-cracks. After immersion in the DAP solution for 24 hours, the samples were rinsed with deionized water to remove excess DAP and dried at room temperature. The consolidating action of the HAP-treatment was assessed by measuring the increase in E_d , which is often used to evaluate the ability of consolidants to re-establish the cohesion between grains^{13,36}. It is true that an E_d increase might be registered even when micro-cracks are filled with a compound that is not actually bonding the micro-crack surfaces (e.g., soluble salts³⁷), so that no increase in mechanical strength is experienced; however, previous studies have demonstrated that E_d increases owing to HAP formation inside the micro-cracks are linked to actual increases in tensile strength¹³ and resistance to abrasion²⁰. The increase in E_d after consolidation was assessed by repeating the E_d measurements. One sample for each condition was also subjected to a second consolidation treatment in the same conditions as above, to check the benefit of double treatments. The consolidating action of the hydroxyapatite formed inside the micro-cracks was also qualitatively assessed by observing a fracture surface of a sample preliminarily damaged at 200 °C and then

treated once. A field emission gun environmental scanning electron microscope (FEG-ESEM, FEI Quanta 200) was used.

4. RESULTS AND DISCUSSION

4.1. Temperature dependence of the thermal diffusivity

The profiles of temperature increase registered by the 6 thermocouples during the heating experiments are reported in Figure 3, for a sample slowly heated to 400 °C by contact with a plate initially cold, and in Figure 4, for a sample rapidly heated to 400 °C by contact with a plate initially at 200 °C. In both cases, as expected, the final maximum temperature is lower at increasing depth from the plate; however, when the lower surface reached 400 °C, in the case of slow heating the sample top reached a temperature above 200 °C, whereas in the case of fast heating the sample top is well below 100 °C.

By solving Eq. (1) numerically, a rather good fit to the experimental data was obtained for both slow and fast heating (Figure 3 and Figure 4, where black curves indicate the experimental data and the red dotted curves indicate the fit). However, the k_1 , k_2 and λ_k parameters necessary to describe the temperature-dependence of k with Eq. (2) were significantly different for slow and fast heating rates. Specifically, fits to the three experiments with slow heating provided a substantially identical trend of k versus temperature, but the experiments with fast heating provided a significantly different trend, as shown in Figure 5a.

When the joint fit is performed with properties described by Eq. (5), better results are achieved, as illustrated in Figure 6. Although improved compared to fits using Eq. (1) (reported in Figure 5b), the fit is imperfect, particularly at early times. This is unfortunate because, for the purpose of producing artificially aged samples with a gradient in properties, the contact time with

the hot plate is expected to be quite short (otherwise heat and consequent damage will propagate all through the sample). Nevertheless, the accuracy of the prediction is sufficient for identifying the thermal treatment needed to achieve the desired level of damage, as demonstrated in § 4.3.

4.2. Temperature dependence of dynamic elastic modulus

The decrease in E_d with temperature is illustrated in Figure 7, where the dots are the experimental values and the curve is a fit to Eq. (3). The reduction in E_d (from an initial value of $E_0 \approx 65$ GPa) as temperature increases is due to the formation of new micro-cracks that open at grain boundaries as a result of anisotropic thermal expansion of the calcite crystals, leading to a loss of cohesion between grains¹. Notably, after heating to 200 °C the E_d is already reduced to 30% of its initial value and heating to higher temperature causes a relatively small additional damage. This high sensitivity to temperature (much more pronounced than that measured in a previous study on limestone¹³) is a consequence of the very tight packing of calcite grains in unweathered marble, so that no grain deformation upon heating can take place without causing stress¹⁹.

4.3. Validation of the mathematical model

The level of damage that we wanted to reproduce was based on the characterization of a naturally weathered marble sample analyzed in a previous study²⁰. After exposure in the field for some 150 years, the E_d of this marble sample had decreased by ~40% in the first 1 cm from the surface, by ~10% between 1 and 2 cm and was basically unchanged at greater depth²⁰. Considering the intrinsic variability of damage from case to case, for simplicity's sake a reduction in E_d of ~40% in the first 1 cm, with no damage at greater depth, was chosen as the target in the present study. The mathematical model predicts that a sample put in contact with a hotplate at 200 °C for 20 seconds will experience a 70% decrease in E_d at the surface and no decrease at a depth of 1 cm,

corresponding to an average 35% decrease in the first 1 cm. To verify the model predictions, 3 samples ($5 \times 5 \times 1 \text{ cm}^3$) were damaged by contact with a hotplate at 200°C for 20 seconds and the consequent E_d decrease was determined. The E_d measurement was performed in the first 1 cm from the $5 \times 1 \text{ cm}^2$ surface in contact with the hot plate and at a distance of 4 to 5 cm from the heated surface, to verify that this part was not damaged, as foreseen by the model. More refined profiling of E_d (at distances between 1 and 4 cm from the heated surface) was not possible because of the size of the available transducers (5 cm). By putting only the most external 1 cm part of the samples between the transducers, it was possible to reliably measure E_d in these external parts, but no information could be obtained between 1 and 4 cm from the heated surface. To verify the versatility of the model, 3 other samples were damaged in more severe conditions (300°C for 20 seconds) and then again the E_d decrease predicted by the model was verified experimentally.

The comparison between the E_d decrease predicted by the model and measured experimentally is illustrated in Figure 8. On the surface, E_d is predicted to be reduced to 30% and 15% of its initial value after heating at 200°C and 300°C , respectively, in accordance with the $E_d[T]$ relationship reported in Figure 7. For both heating temperatures, the damage is predicted to be mostly limited to the first 1 cm from the plate, whereas the remaining part of the sample should remain unaltered (Figure 8a). According to the model, in the first 1 cm the average value of E_d is expected to be reduced to 65% of its initial value (35% E_d reduction) after heating at 200°C , and to 58% (42% E_d reduction) after heating at 300°C (Figure 8b). When the same conditions of heating temperature and time were adopted experimentally to produce aged samples, the values of E_d decrease reported in Figure 8b were obtained. In both conditions, the experimental results exhibited very good agreement with what was predicted by the model.

Additional macroscopic evaluation of the depth of damage induced by heating at 200°C and 300°C for 20 seconds was obtained by placing a drop of methylene blue solution (10 g/L) onto

the sample face that had been put in contact with the hotplate. After drying, the depth of penetration of the methylene blue solution into the micro-cracks developed after artificial weathering was evaluated. Cross sections of the stained samples were obtained by dry sawing (to avoid solubilizing the methylene blue stain) and by fracturing with a chisel.

The cross sections of unweathered and weathered samples are illustrated in Figure 9a. Because holes with 3 mm diameter had been drilled starting from the heated surface toward the interior, the depth of the methylene blue stain can be observed in the internal surface of these holes. (The holes had been drilled in hopes of assessing the variation in micro-drilling resistance with depth. However, for the given specimen size and marble grain size, the results obtained with the available instrument exhibited very high scatter, even in the unweathered specimens. This made it impossible to reliably assess any variation of the micro-drilling resistance with depth in the weathered samples.) As a consequence of the micro-cracks opened after the accelerated ageing procedures, the depth of penetration of the methylene blue solution into the thermally aged samples was markedly higher than in the fresh sample. In the aged samples, the staining gradually decreased from the heated surface towards the interior, a slight color difference being still visible at 1 cm depth, as expected. On the contrary, in the fresh sample the staining was barely visible. In terms of penetration depth, the two samples heated at different temperatures do not exhibit a dramatic difference, which is consistent with the prediction by the model. At the same time, the sample heated at 300 °C exhibits more intense staining near the surface, which is consistent with the higher near-surface damage expected in this sample. The difference in the stain color between the two heated samples is due to the different time elapsed between the staining and the observation (a few days in the case of the sample heated at 200 °C, a few hours in the case of the sample heated at 300 °C). A fracture cross-section of the sample heated at 300 °C was also observed against the light: as

illustrated in Figure 9b, a progressive fading of the blue stain was assessed, down to a depth of about 1 cm.

Marble samples artificially damaged by contact with the hotplate exhibit features quite close to those of naturally weathered marble (namely a decrease in E_d of ~40% in the first 1 cm from the surface, while the underlying substrate is still sound²⁰). These samples can therefore be regarded as suitable to investigate the performance of stone consolidants, whose main objective is to re-establish cohesion between grains in the weathered part, without causing over-consolidation (i.e. excessive stiffening) of the sound part^{10,38,39}.

4.4. Consolidation

When samples artificially aged by brief contact with the hotplate at 200°C and 300 °C were treated by the hydroxyapatite treatment, a substantial increase in E_d was achieved in both cases (Figure 10). As expected, the ability to restore the initial E_d was more pronounced in the sample with the least damage (hotplate at 200 °C instead of 300 °C). This increase in E_d (which can be taken as representative of an increase in strength, as discussed in § 3.4) was made possible by formation of hydroxyapatite inside the micro-cracks, as revealed by SEM observation (Figure 11). However, in neither case was the original E_d fully restored in the lower 1 cm. A second consolidation treatment, identical to the first one, was then applied. In the case of the sample decayed at 200 °C (Figure 9,a), E_d was completely restored after the second treatment, with no excessive over-consolidation of the upper sound part (increases in bending strength, compressive strength and modulus of elasticity up to +125% of the undamaged value⁴⁰ and increases in tensile strength up to +150%⁴¹ of the undamaged value have been identified in the literature as thresholds beyond which consolidation is excessive – the same percentage increases were assumed here as references to evaluate the E_d increases, which resulted always lower than any of these thresholds).

The results achieved on this sample, initially exhibiting a damage condition very close to that of naturally weathered marble, indicate that the treatment with hydroxyapatite consolidant is suitable, being both effective in enhancing mechanical properties and compatible from a mechanical point of view, as it does not cause over-consolidation. In the case of the sample decayed at 300 °C, the second treatment raised E_d up to 93% of its initial level. Although not complete, this increase in mechanical properties can be considered satisfactory as well, considering that this sample had been weathered to a higher (but still realistic) extent compared to the sample coming from the field.

5. CONCLUSIONS

In this paper, a novel method for accelerated aging of marble was proposed, to produce samples with a gradient in properties resembling the condition of marble elements exposed outdoors (characterized by more diffused micro-cracking near the surface). Based on the results of the study, the following conclusions can be derived:

- 1) The mathematical model, which takes into account the dependence of the thermal diffusivity, thermal expansion coefficient, and dynamic elastic modulus upon temperature, allows prediction of the mechanical damage occurring in marble samples put in contact with a hot plate at a certain temperature for a certain time. Results obtained experimentally provided good confirmation of the model predictions. However, because of the limitation coming from the size of the available transducers (which do not provide sufficient spatial resolution), more detailed validation of the model seem opportune. In a future study, it would be ideal to obtain a profile of the damage to the stone (e.g., by using microindentation test).
- 2) To produce damage similar to that encountered in the field (e.g. a decrease in dynamic elastic modulus E_d of ~40% in the first 1 cm from the surface and no damage in the underlying

marble), the model prescribes that Carrara marble samples be put in contact with a hotplate at 200 °C for 20 sec. When these conditions were adopted experimentally, a very good agreement was found between the E_d decrease predicted by the model in the first 1 cm of the sample (-35%) and that measured experimentally (-38%). Similarly, when a more severe weathering condition (heating at 300 °C for 20 sec) was used to check the model versatility, very good agreement was again found between the calculated (-42%) and the measured (~44%) values of E_d decrease. This confirms the suitability of the mathematical model for preparing samples with a desired gradient in mechanical properties. The depth of damage was verified by penetration of dye, which indicated a gradient in damage extending to a depth of about 1 cm.

- 3) The hydroxyapatite-based treatment, used to demonstrate the suitability of thermally aged samples for testing of consolidants, proved to be effective in improving the dynamic elastic modulus (completely restored after a double application) and compatible from a mechanical point of view (as it did not cause any excessive over-consolidation of the sound part of the sample).

In the case of other varieties of marble (including dolomitic marble), the properties of the specific lithotype would be needed to suitably adjust the mathematical model and obtain accurate predictions of the heating temperature and time. However, in case detailed property data are not available, the results of the present paper can be taken as a starting point and the appropriate time of contact for a different lithotype can be found by simple empirical tests.

The mathematical model developed in this paper can be applied to other polycrystalline materials, including ceramics, as well as natural stone, that develop internal stresses owing to anisotropic thermal and elastic properties. To obtain an analytical solution for such a complex problem requires severe assumptions (treating each grain as a sphere surrounded by an isotropic polycrystalline shell, and accounting for macroscopic thermal stresses by imposing the hydrostatic

component on the composite sphere), so the results are highly approximate. The virtue of the method is that attributing the change in thermal properties to the magnitude of the strain energy explains why cooling is as damaging as heating. Moreover, the accuracy is sufficient to allow adequate prediction, using a single set of parameters, of the temperature distribution in marble samples heated slowly or rapidly.

ACKNOWLEDGMENTS

This project has received funding from the European Union's Horizon 2020 research and innovation program under the Marie Skłodowska-Curie grant agreement N. 655239 (HAP4MARBLE project, "*Multi-functionalization of hydroxyapatite for restoration and preventive conservation of marble artworks*").

REFERENCES

1. Siegesmund S, Ullemeyer K, Weiss T, Tschegg EK. Physical weathering of marbles caused by anisotropic thermal expansion. *Int. J. Earth Sci.* 2000;89:170-182.
2. ICOMOS (International Scientific Committee for Stone). Illustrated glossary on stone deterioration patterns. Champigny/Marne, France: Ateliers 30 Impression, 2008; p. 20-21.
3. Charola AE, Centeno SA, Normandin K. The New York Public Library: protective treatment for sugaring marble. *J. Archit. Conserv.* 2010;16:29-44.
4. Sàez-Pèrez MP, Rodríguez-Gordillo J. The influence of solar radiation on the deterioration of the marble columns in the Courtyard of the Lions In The Alhambra, *Stud. Conserv.* 2008;53:145-157.

5. Sassoni E, Franzoni E. Sugaring marble in the Monumental Cemetery in Bologna (Italy): characterization of naturally and artificially weathered samples and first results of consolidation by hydroxyapatite, Appl. Phys. A-Mater. 2014;117:1893-1906.
6. Lord Rayleigh. The Bending of Marble. Proceedings of the Royal Society of London. Series A, Containing Papers of a Mathematical and Physical Character 1934;144:266-279.
<http://www.jstor.org/stable/2935557>
7. Royer-Carfagni G. Some considerations on the warping of marble façades: the example of Alvar Aalto's Finland Hall in Helsinki," Const. Build. Mater. 1999;13:449-457.
8. Siegesmund S, Ruedrich J, Koch A. Marble bowing: comparative studies of three different public building facades. Environ. Geol. 2008;56:473-494.
9. Marini P, Bellopede R. Bowing of marble slabs: evolution and correlation with mechanical decay. Constr. Build. Mater. 2009;23:2599-2605.
10. Amoroso GG, Fassina V. Stone decay and conservation. New York, USA: Elsevier; 1983.
11. Hansen E, Dohene E, Fidler J, Larson J, Martin B, Matteini M, et al. A review of selected inorganic consolidants and protective treatments for porous calcareous materials. Reviews in conservation. 2003;4:13-25.
12. Wheeler GS. Alkoxysilanes and the consolidation of stone. Los Angeles, USA: The Getty Conservation Institute; 2005.
13. Sassoni E, Naidu S, Scherer GW. The use of hydroxyapatite as a new inorganic consolidant for damaged carbonate stones. J. Cult. Herit. 2011;12:346-355.
14. Wheeler GS, Fleming SA, Ebersole S. Evaluation of some current treatments for marble. In: La conservation des monuments dans le bassin mediterraneen: Actes du 2^o symposium international [The conservation of monuments in the Mediterranean Basin: Proceedings of the 2nd International Symposium]; 19-21/11/1991; Geneve, Switzerland; 1992;p. 439-443.

15. Franzoni E, Sassoni E, Scherer GW, Naidu S. Artificial weathering of stone by heating. *J. Cult. Herit.* 2013;14S:e85-e93.
16. Lubelli B, van Hees RPJ, Nijland TG, Bolhuis J. A new method for making artificially weathered stone specimens for testing of conservation treatments. *J. Cult. Herit.* 2015;16:698-704.
17. Sena da Fonseca B, Ferreira Pinto AP, Piçarra S, Montemor MF. Artificial aging route for assessing the potential efficacy of consolidation treatments applied to porous carbonate stones. *Mater. Design* 2017;120:10-21.
18. Franzoni E, Sassoni E. Comparison between different methodologies for artificial deterioration of stone aimed at consolidants testing. In: *Proceedings of the 12th International Congress on Deterioration and Conservation of Stone*. New York City, USA; 2012. <http://iscs.icomos.org/pdf-files/NewYorkConf/fransass.pdf>
19. Sassoni E, Franzoni E. Influence of porosity on artificial deterioration of marble and limestone by heating. *Appl. Phys. A-Mater.* 2014;115:809–816.
20. Sassoni E, Graziani G, Franzoni E. Repair of sugaring marble by ammonium phosphate: comparison with ethyl silicate and ammonium oxalate and pilot application to historic artifact. *Mater. Design* 2015;88:1145-1157.
21. Hanley EJ, Dewitt DP, Roy RF. The thermal diffusivity of eight well-characterized rocks for the temperature range 300-1000 K. *Eng. Geol.* 1978;12:31-47.
22. Shushakova V, Fuller Jr ER, Siegesmund S. Microcracking in calcite and dolomite marble: microstructural influences and effects on properties. *Environ. Earth Sci.* 2013;69:1263–1279.
23. Walsh JB. Theoretical bounds for thermal expansion, specific heat, and strain energy due to internal stress. *J. Geophys. Res.* 1973;87:7637-7646.

24. Budiansky B., O'Connell RJ. Elastic moduli of a cracked solid. *Int. J. Solids Structures* 1976;12:81-97.
25. Weiss T, Rasolofosaon PNJ, Siegesmund S. Ultrasonic wave velocities as a diagnostic tool for the quality assessment of marble. In: Siegesmund S, Weiss T, Vollbrecht A, eds. *Natural stone, weathering phenomena, conservation strategies and case studies*. Geological Society, London, Special Publications 2002;205:149-164.
26. Luque A, Ruiz-Agudo E, Cultrone G, Sebastián E, Siegesmund S. Direct observation of microcrack development in marble caused by thermal weathering. *Environ. Earth Sci.* 2011;62:1375-1386.
27. Ruedrich J, Knell C, Enseleit J, Rieffel Y, Siegesmund S. Stability assessment of marble statues of the Schlossbrücke (Berlin, Germany) based on rock strength measurement and ultrasonic wave velocities. *Environ. Earth Sci.* 2013;69:1451–1469.
28. Mahmutoğlu Y. Prediction of weathering by thermal degradation of a coarse-grained marble using ultrasonic pulse velocity. *Environ. Earth Sci.* 2017;76:435.
29. Naidu S, Blair J, Scherer GW. Acid-resistant coatings on marble. *J. Am. Ceram. Soc.* 2016;99:3421-3428.
30. Olsson DM. A sequential simplex program for solving minimization problems. *J. Qual. Technol.* 1974;6:53-57.
31. Sassoni E, Graziani G, Franzoni E, Scherer GW. Some recent findings on marble conservation by aqueous solutions of diammonium hydrogen phosphate. *MRS Advances* 2017;2:2021-2026.
32. Naidu S, Sassoni E, Scherer GW. New treatment for corrosion-resistant coatings for marble and consolidation of limestone. In: *Jardins de Pierres – Conservation of stone in Parks, Gardens and Cemeteries*. Paris, France; 2011:p. 289-294.

33. Naidu S, Scherer GW. Nucleation, growth and evolution of calcium phosphate films on calcite. *J. Colloid. Interf. Sci.* 2014;435:128-137.
34. Graziani G, Sassoni E, Franzoni E, Scherer GW. Hydroxyapatite Coatings For Marble Protection: Optimization Of Calcite Covering And Acid Resistance. *Appl. Surf. Sci.* 2016;368:241-257.
35. Ji X, Su P, Liu C, Li J, Tan H, Wu F, et al. A novel ethanol induced and stabilized nanorods: hydroxyapatite nanopeanut. *J. Am. Ceram. Soc.* 2015;98:1702-1705.
36. Ruedrich J, Weiss T, Siegesmund S. Thermal behavior of weathered and consolidated marbles. In: Siegesmund S, Weiss T, Vollbrecht A, eds. Natural stone, weathering phenomena, conservation strategies and case studies. Geological Society, London, Special Publications 2002;205:255-271.
37. Sassoni E, Graziani G, Franzoni E. An innovative phosphate-based consolidant for limestone. Part 2: Durability in comparison with ethyl silicate. *Const. Build. Mater.* 2016;102:931-942.
38. Italian Recommendation NORMAL 20/85. Conservazione dei materiali lapidei: Manutenzione ordinaria e straordinaria [Conservation of stone materials: ordinary and extraordinary maintenance]. Rome, Italy: Istituto Centrale per il Restauro (ICR), 1985.
39. Sassoni E, Graziani G, Franzoni E. An innovative phosphate-based consolidant for limestone. Part 1: effectiveness and compatibility in comparison with ethyl silicate. *Constr. Build. Mater.* 2016;102:918-930.
40. Delgado Rodrigues J, Grossi A. Indicators and ratings for the compatibility assessment of conservation actions. *J Cult Herit* 2007;8:32-43.
41. Maravelaki-Kalaitzaki P, Kallithrakas-Kontos N, Korakaki D, Agioutantis Z, Maurigiannakis S. Evaluation of silicon-based strengthening agents on porous limestones. *Prog. Org. Coat.* 2006;57:140-148.




Figure 1. SEM image illustrating marble microstructure and grain size.




Figure 2. Cartoon illustrating the experimental set up used to determine the thermal diffusivity k .
a) Grooves were cut in marble samples to allow insertion of thermocouples at increasing distance from the plate; b) the samples with the grooves were coupled with others without grooves to form “sandwich samples”; c) the “sandwich samples” were instrumented with 6 thermocouples and insulated with a high temperature-resistant insulator (not illustrated in the picture). In this way, the temperature increase as a function of time and distance from the plate was measured.




Figure 3. Temperature increase as a function of time and distance from the heating plate, for a sample slowly heated to 400 °C by contact with a plate initially at room temperature (black curve = experimental data; red dotted curve = fit).




Figure 4. Temperature increase as a function of time and distance from the heating plate, for a sample rapidly heated to 400 °C by contact with a plate initially at 200 °C (black curve = experimental data; red dotted curve = fit).




Figure 5. Results of the separate fit: (a) trend of k variation with temperature, as calculated by fitting separately using Eq. (1) (the solid curves are best fits for samples heated slowly, while the dashed curve is for the sample heated quickly on a hotplate preheated to 200 $^{\circ}\text{C}$); (b) temperature increase as a function of time and distance from the heating plate, for a sample rapidly heated to 400 $^{\circ}\text{C}$ by contact with a plate initially at 200 $^{\circ}\text{C}$, as determined experimentally (bold dots) and calculated (dashed curves) by using the k function obtained from the separate fit.




Figure 6. Results of the joint fit: (a) the function ψ , which governs the behavior of the thermal diffusivity of the marble matrix; (b) temperature increase as a function of time and distance from the heating plate, for a sample rapidly heated to 400 °C by contact with a plate initially at 200 °C, as determined experimentally (bold dots) and calculated (dashed curves) by using the function ψ in a joint fit of all the tests.




Figure 7. Reduction in dynamic elastic modulus E_d as a function of heating temperature.




Figure 8. Reduction in dynamic elastic modulus E_d after heating at 200 °C and 300°C for 20 seconds: a) profile of E_d decrease predicted by the mathematical model as a function of the distance from the heating plate; b) comparison between the average E_d decrease predicted in the lower and upper 1 cm of the sample and that measured experimentally.




Figure 9. Depth of penetration of the methylene blue solution: a) comparison between fresh marble and marble aged at 200° and 300 °C for 20 seconds (the difference in color between the stain in the samples heated at 200 and 300 °C is due to the different time elapsed between the staining and the observation: a few days in the former case, a few hours in the latter case); b) depth of penetration in the sample heated at 300 °C, as assessed by observing a fracture cross section against the light.




Figure 10. Variations in dynamic elastic modulus E_d after accelerated aging by heating at 200 °C for 20 sec (a) and 300 °C for 20 sec (b) and after consolidation by the hydroxyapatite-treatment, applied once and twice.




Figure 11. SEM images of a marble sample pre-weathered by heating on a hotplate at 200 °C for 20 sec and then subjected to the hydroxyapatite-treatment. Magnification: a) 1000×, b) 5000× (detail of the area identified in a)).